

PRODUCT DATA SHEET

GREY CLOTH DUCT TAPE

PRODUCT DESCRIPTION:

PE-coated cloth Tape with a pressure sensitive rubber adhesive coating combined to provide a quality product.

It is a good choice for bundling, heavy carton packing, general maintenance, pipe wrapping, carpet fixing, air-conditioning ducts seam and joint sealing etc.

FEATURES:

- High Tensile Strength.
- Excellent Moisture Resistant, Easy Tear and Conforms well to irregular surfaces.
- Water resistant backing.
- Service Temperature range from -20° to +60°C (-4° to +140°F).

TYPICAL PHYSICAL PROPERTIES:

PE Film Thickness	50 Micron	
Total Thickness	178 Micron	
Reinforcement	PET Cloth	
Tensile Strength	74 N/25mm	PSTC-31
Elongation	15%.	
Adhesive	Natural Rubber / Resin	
Adhesion to Steel (in of Width)	41 (11 N/25mm)	PSTC-1
Quick Stick to Steel (in of width)	13.5 (3.7N/25mm)	PSTC-33
Colour	Silver Grey	

TYPICAL APPLICATIONS:

Packaging, Wrapping & Sealing, Binding & Bundling, General Maintenance, Pipe Wrapping, Carpet Fixing, Air-Conditioning Duct's Seam and Joint Sealing .

STORAGE & SHELF LIFE:

Product should be stored in a cool, dry area in original packing and to use within 12month of shipment n stored at 21°C (70°F) / 50% relative humidity out of direct sunlight.

SURFACE PREPARATION:

It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied must be clean, dry, and free of grease, oil or other contaminants.

PRODUCT USE:

It is essential that the user evaluate the Asmaco tape product to determine whether it is fit for a particular purpose and user's method of application. Good results will be obtained when applied to a clean, dry surface with a suitable pressure on the Asmaco **Tape** product between +10 ~ +60°C (+50 ~ +140 °F).

LIMITED WARRANTY & LIMITED REMEDY:

Your exclusive remedy & Asmaco **Tape** obligation shall be, at Anchor Allied Factory's option, to replace or repair the product or refund the purchase price of the product.

NOTE

The information and data contained in the product data sheet is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of the product for usage. Since the supplier cannot know all the uses, or the conditions of use to which the product may be exposed, no warranties concerning the fitness or suitability for particular use or purpose are made. It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application Likewise if the application, product specifications or manner in which our products are used require government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

Non – warranty: Because the storage, handling and application of the material is beyond Anchor Allied Factory Ltd's control, we can accept no liability for the result obtained. Anchor Allied Factory Ltd's sole limited warranty is the product meets the manufacturing specifications in effect at the time of shipment. There is no warranty or merchantability or fitness for use, nor any expressed or implied warranty. Anchor Allied Factory Ltd will not be liable for any incidental and consequential damage of any kind. The exclusive remedy for breach of such limited warranty is a replacement of any product shown to be other than warranted. Suggestions of uses should not be taken as inducement to infringe any patents.