



Product Data Sheet

ASMACOAT WP 936

One-Component, Aliphatic, Elastic Polyurethane Liquid Applied Waterproofing Membrane

DESCRIPTION:

ASMACOAT WP 936 is a top-tier protective coating formulated with Aliphatic Polyurethane Resins. Its one component design allows application on diverse surfaces, including steel, concrete, and cured epoxies or Polyurethanes. Applying two coats with a wet film thickness of 250-300 microns per coat results in a final dry film thickness of 150-180 microns. This coating excels in extreme exposure conditions, and additional coats may be applied for enhanced protection. ASMACOAT WP 936 stands out as a high-performance solution, ensuring robust defence against environmental elements.



KEY PERFORMANCE PROPERTIES

When applied, forms a seamless membrane without joints or leak possibilities

- Excellent crack bridging properties
- Easy application
- UV Resistant and withstands extreme weather conditions
- Provides glossy and easy-to-clean surface
- Offers excellent durability and superior abrasion resistance

AREAS OF APPLICATION

ASMACOAT WP 936 can be successfully applied on tiles, concrete, cement roof tiles, wood and galvanized steel. The seamless membrane can be used as an impervious waterproof coating on the following:

- Roofs
- Sunken Slabs
- Concrete Domes
- Profile Sheets
- Kitchen and Bathrooms
- Balconies and Patios
- Basements
- Swimming Pools and other Water Retaining
- Structures, Bridges and Tunnels, etc.

METHOD OF APPLICATION

ASMACOAT WP 936 shall be applied as per the following general method of application.

Surface Preparation:

The surface of the concrete shall be sound, clean and uncontaminated. This preparation shall be such as to leave a sound exposed concrete surface free from dust, loose particles and any deleterious matter. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Oil, grease, varnishes, rust, dust and mould on metal surfaces shall be removed by wire or stiff brushing and grit blasting then wiped with solvent prior to priming.

New concrete or cementitious surfaces should be at least 28 days old and have moisture content not exceeding 5%. Old or existing surface should be refurbished mechanically to ensure clear and sound substrate.

Crack Treatment

Shrinkages and non-moving structural cracks less than 1.0 mm shall be filled with a pre-treatment ASMACO POXY 90 FC of 1.0mm thick extended to 75 mm on both sides of the crack. Voids and honeycombs shall be patched, before applying the membrane.

Right Angle Bends

All rightangle bends must have a coving detail installed. In areas where parapet walls, columns, pipe penetration are present, a 45° coving fillet shall be made at all corners using FIBER MESH. All other angles, joints, protrusions and stress joints should be pre-treated with a heavy application of ASMACOAT WP 936 extending 150 mm on both sides of the coving.

Movement Joints

Expansion and movement joints should be sealed with ASMACO PU 90 SP, Polyurethane sealant. When cured a stripped layer ASMACOAT WP 936, 200mm wide shall be applied and centred all over the sealed joints.



Product Data Sheet

Allow to cure before the general application. While the membrane is still wet cover with a correct cut strip of fiber mesh and press it to soak. Saturate the fiber mesh with another coat of ASMACOAT WP 936 until it is fully covered. Allow curing before applying further coats of the waterproofing membrane.

Priming

Highly porous concrete or concrete containing micro silica will be primed using ANCHOR PRIMER P1 solvent based epoxy primer. The primer shall be applied at a rate of 5-6m²/L. Primer should be left to achieve a tack-free condition for 6-8 hours before applying the top coat. A second coat of primer may be required if the substrate is excessively porous.

Mixing

ASMACOAT WP 936 should be stirred before use until a uniform color and consistency is achieved. Product is ready for use.

Application

ASMACOAT WP 936 shall be applied by brush, roller, trowel or airless spray in 2 coats to achieve a minimum dry film thickness of 1.0 mm for each coat. The two coats must be applied at right angles to one another. A layer of fiber glass mesh should be embedded between the two ASMACOAT WP 936 coats over pipe culverts, floor, drains, corner joints and floor / wall junctions.

The final wet coat of ASMACOAT WP 936 shall be spread with sufficient clean silica and before applying tile adhesives. Tiling or finished floor installations should be carried out as soon as possible after full cure of membrane.

PACKAGING

ASMACOAT WP 936 is available in 28 Kg Pail

COVERAGE RATE

1.4 Kg / m² / 1mm, Thickness

STORAGE & SHELF LIFE

Store in cool place under cover, out of direct sunlight and protect from extreme temperatures. In tropical climate the product must be stored in air – conditioned environment (<25° C). The shelf life is up to 12 months in unopened conditions if stored as per guidelines.

IMPORTANT NOTE

Do not dilute, this is ready to use solution for application. Do not apply if rain or possibility of rain within next 48. hours as the product is not resistant to rain during application until fully dry.

CLEAN UP

Tools and equipment used for application of ASMACOAT WP 936 should be cleaned with ASMACO CLEANER 2 after the usage.

HEALTH & SAFETY

ASMACOAT WP 936. During application, wear appropriate protective clothing, goggles, gloves, and respiratory equipment if necessary. In case of contact with skin, rinse with water and again wash thoroughly with soap and water. In case of contact with eyes, rinse with plenty of water and seek medical advice accordingly. If ingested, obtain medical assistance on immediately. Do not induce vomiting. In case the material splashes to the skin or eyes wash the same with fresh water immediately.

In critical cases seek medical assistance.



Product Data Sheet

TECHNICAL SPECIFICATION

PROPERTIES	TYPICAL VALUES	TEST STANDARDS
Color	White & Other Colors on Request	-
Full cure	7 days @ 25°C	-
Service temperature	-5°C to +80°C	-
Application Temp	5°C to + 45°C	-
Tack Free Time	5 Hours @ 25 °C	-
Density,	~1.4 g/cc	ASTM D 1475
Tensile strength	>15 N/mm ²	ASTM D 412
Elongation at break	>500 ± 5 %	ASTM D 412
Tear Resistance	>10 N/mm ²	ASTM D 624
Crack Bridging	No loss on bond, after extension of 2.5 mm	ASTM C 836
Water Vapour Transmission	0.3 g/h.m ² (24 Hours)	ASTM D 2939
Shore A Hardness	40 - 50	ASTM D 2240

All values given are subject to 5-10% tolerance and under standard lab conditions.

Shipping Limitations: None

Note

The information and data contained in the product data sheet is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of the product for use. Since the supplier cannot know all the uses, or the conditions of use to which the product may be exposed, no warranties concerning the fitness or suitability for particular use or purpose are made. It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application. Likewise if the application, product specifications or manner in which our products are used require government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

Non – Warranty : Because the storage, handling and application of the material is beyond Anchor Allied Factory Ltd's control, we can accept no liability for the result obtained. Anchor Allied Factory Ltd's sole limited warranty is the product meets the manufacturing specifications in effect at the time of shipment. There is no warranty or merchantability or fitness for use, nor any expressed or implied warranty. Anchor Allied Factory Ltd will not be liable for any incidental and consequential damage of any kind. The exclusive remedy for breach of such limited warranty is a replacement of any product shown to be other than warranted. Suggestions of uses should not be taken as inducement to infringe any patents.

All ANCHOR ALLIED FACTORY LLC datasheets are updated on a regular basis. This technical data sheet supersedes all previous editions relevant to this product. It is the user's responsibility to obtain the recent version.



☎ : +971 6 5342091, 📠 : +971 6 5342107, P.O. Box No.: 21152

MFG. OF SILICONE , ACRYLIC & POLYURETHANE SEALANTS, WATER PROOFING COATINGS,
SELF - ADHESIVE TAPES, SPRAY PAINTS, CONTACT ADHESIVE, PVC CEMENTS, EPOXY STEEL

Rev 02, TDS_ASMACOAT WP 936, GCC 0125

📍 Industrial Area-15, Sharjah, U.A.E. 🌐 www.anchorallied.com ✉ info@anchorallied.com