



Product Data Sheet

ASMACOAT WP 600

Acrylic Liquid Applied Waterproofing Membrane

DESCRIPTION:

ASMACOAT WP 600 is a one component acrylic liquid applied waterproofing and protective coating for concrete and recommended substrate structures. A water based acrylic liquid applied membrane. It is easily applicable on horizontal and vertical surfaces. Once cured it forms a continuous waterproofing membrane resistant against the thermal changes and the ultraviolet rays. Suitable for use in hot and tropical climate conditions.



KEY PERFORMANCE PROPERTIES

- UV resistant and resistant to yellowing and weathering
- Highly elastic and crack-bridging
- One component - ready to use
- Excellent adhesion on porous and non-porous substrates
- Seamless, fully bonded waterproofing membrane
- Water vapour permeable

AREAS OF APPLICATION

ASMACOAT WP 600 is easy to apply, cost effective and particularly used in:

- Concrete roofs, metal profile roofs, asbestos roofs, domes
 - Protective coating for Polyurethane sprayed foam against UV effect
 - Protective coatings on underpasses & concrete bridge decks.
- For reflective coating to enhance energy efficiency by reducing cooling costs.

- Roofs, terraces & balconies.
- Protective and decorative coating on exposed concrete surfaces both for vertical and horizontal applications.
- Waterproofing of flashing, roof edgings, walls (either concrete, cement mortar, wood, or metal),

METHOD OF APPLICATION

ASMACOAT WP 600 shall be applied as per the following general method of application.

A. Substrate preparation:

The performance and ultimately durability of the coating largely depends on the condition of the substrate. Therefore, conditioning and preparation of the substrate is of utmost importance.

Concrete surface:

The surfaces shall be thoroughly cleaned to remove all dust particles and laitance. Surface defects like potholes and pinholes on building facades on the concrete shall be repaired with an appropriate polymer modified repair mortar.

Metal surface:

The surface should be cleaned from all rust scales. This can be achieved by wire brushing or grit blasting.

B. Priming

On new concrete surface the **ASMACOAT WP 600** coating can be applied directly. However, it is highly recommended to apply a priming coat on all old and porous substrates for improving the adhesion of the subsequent coats.

The priming coat can be prepared in the work site by diluting **ASMACOAT WP 600** with only 30% clean potable water. The priming material shall be mixed thoroughly using a low RPM paddle mixer to ensure proper homogeneity of the mix. Primer application can be done using a brush or roller. For large areas the application can also be done using an airless spray machine. The primer should be allowed to dry before applying subsequent coats for at least 6 to 8 hours. The area should be re-primed if there is a delay in the application of the topcoat for more than 24 hours depending on the area of application and the nature of the substrate.

Rev 02, TDS_ASMACOAT WP 600, GCC 1124



Product Data Sheet

For higher strength and flexibility, insert a non-woven geotextile membrane whilst the first coat is still wet on all corner joints, fillets, and pipe penetration joints. Allow the coating to fully cure for 72 hours to achieve its full properties.

C. Mixing:

When a container is opened, the contents may have settled or separated over time, especially if the product has been sitting on a shelf or in storage for a while. Mixing the contents thoroughly can help to recombine any separated components and ensure that the product is at its intended consistency.

D. Topcoat

Application of **ASMACOAT WP 600** is to be done by using a suitable roller or brush. Large areas of application can be done by using an airless spray machine.*

The coating always must be applied with a minimum of 2 coats for optimum performance. The coverage rate will always vary depending on the area of application and the nature of the substrate
Re-coat Interval 6 hours @ 40 °C.

For **higher strength** and flexibility, insert a non-woven geotextile membrane whilst the first coat is still wet on all corner joints, fillets, and pipe penetration joints. Allow the coating to fully cure for 7 days to achieve its full properties.

IMPORTANT NOTE

ASMACO WP 600 is ready to use solution for application. Do not apply if rain or possibility of rain within next 48. hours as the product is not resistant to rain during application / until fully dry.

CLEAN UP

Clean roller brush and equipment after use with warm soap water.

PACKAGING

ASMACOAT WP 600 is available in 20 kg Pail.

COVERAGE RATE

1st Coat 0.7 Kg / m²

2nd Coat 0.6 Kg / m²

Recommended thickness to achieve the required characteristics
≈1000 microns.

Some substrates will require higher consumption than indicated above. This figure is theoretical and does not include for any additional material required due to surface porosity, surface profile,

HEALTH & SAFETY

Protective clothing such as gloves and goggles should be worn while applying **ASMACOAT WP 600**. In case the material splashes to the skin or eyes wash the same with fresh water immediately.

In critical cases seek medical assistance.

STORAGE & SHELF LIFE

Store in cool place under cover, out of direct sunlight and protect from extreme temperatures. In tropical climate the product must be stored in air – conditioned environment (<25° C). The shelf life is up to 12 months in unopened conditions if stored as per guidelines.



Product Data Sheet

TECHNICAL SPECIFICATION

PROPERTIES	TYPICAL VALUES	TEST STANDARDS
Color	Off White/Grey/Other color on request	-
Full cure	72 hours.	-
Service temperature	-5°C — +70°C	-
Application Temp	+5°C — +45°C	-
Solar Reflectivity	Excellent	-
Density,	~1.55 kg/Liter	ASTM D 1475
Solid Content	>70 %	ASTM D 1644
Tensile strength	>1.5 N/mm ²	ASTM D 412
Elongation at break	>200%	ASTM D 412
UV Resistance	Pass	ASTM G 154
Hydrostatic pressure @ 5 bar (50m)	No Leakage	BS EN 12390
VOC	< 27 g/ltr	ASTM D 3960
Peel Adhesion	>0.8 N/mm ²	ASTM D 4541
Crack Bridging	>1.25 mm	ASTM C 836
Solar Reflction Index (SRI)	>90	ASTM C 1549
Shore A Hardness	60 — 65	ASTM D 2240

All values given are subject to 5-10% tolerance.

Shipping Limitations: None

Note

The information and data contained in the product data sheet is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of the product for usage. Since the supplier cannot know all the uses, or the conditions of use to which the product may be exposed, no warranties concerning the fitness or suitability for particular use or purpose are made. It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application. Likewise if the application, product specifications or manner in which our products are used require government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

Non – Warranty : Because the storage, handling and application of the material is beyond Anchor Allied Factory Ltd's control, we can accept no liability for the result obtained. Anchor Allied Factory Ltd's sole limited warranty is the product meets the manufacturing specifications in effect at the time of shipment. There is no warranty or merchantability or fitness for use, nor any expressed or implied warranty. Anchor Allied Factory Ltd will not be liable for any incidental and consequential damage of any kind. The exclusive remedy for breach of such limited warranty is a replacement of any product shown to be other than warranted. Suggestions of uses should not be taken as inducement to infringe any patents.

All ANCHOR ALLIED FACTORY LLC datasheets are updated on a regular basis. This technical data sheet supersedes all previous editions relevant to this product. It is the user's responsibility to obtain the recent version.



☎ : +971 6 5342091, 📠 : +971 6 5342107, P.O. Box No.: 21152

MFG. OF SILICONE , ACRYLIC & POLYURETHANE SEALANTS, WATER PROOFING COATINGS,
SELF - ADHESIVE TAPES, SPRAY PAINTS, CONTACT ADHESIVE, PVC CEMENTS, EPOXY STEEL

Rev 02, TDS_ASMACOAT WP 600, GCC 1124

📍 Industrial Area-15, Sharjah, U.A.E. 🌐 www.anchorallied.com ✉ info@anchorallied.com